



Your Dreams, Our Challenge

Outgassing Data (IPC-TM650 2.6.4B; ASTM E595)

Material	Total Mass Loss TML (1% max)	Collected Volatiles Condensable Material CVCM (0.1% max)	Water Vapor Recovered WVR (No Limits)
ELL	0.34%	0.01%	0.01%
Mercurywave® 9350	0.08%	0.005%	0.04%
Meteorwave® Family	0.09%	0.01%	0.05%
N4000-13 / 13SI	0.37%	0.01%	0.30%
N4000-13EP / EPSI	0.14%	0.01%	0.09%
N4000-29	0.10%	0.01%	0.08%
N4800-20	0.14%	0.01%	0.09%
N5000	0.25%	0.001%	0.23%
N7000-1	0.34%	0.02%	0.34%
N7000-2HT / -3 / -3F	0.47%	0.01%	0.34%
N7000-2V0	0.59%	0.05%	0.48%
N8000	0.019%	0.008%	0.17%

For More Information:

North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.digital-sales@agc.com • www.agc-multimaterial.com

Rev. 11/2022